**ASAP GUN 60 LC** 

## **TECHNICAL DATA SHEET**

**ASAP GUN 60 LC** is a high alumina, very strong; thermal shock resistant, Mullite based low cement gun mix.

**ASAP GUN 60 LC** is recommended for co-gen applications, cement kiln risers, coolers, and curbs or anywhere abrasion or alkali attack is a problem. Heat may be applied faster than traditional heat-up schedules.

**SERVICE TEMPERATURE**: 3000°F

MATERIAL REQUIRED FOR ESTIMATING: 140 lbs./cu. ft. WATER REQUIRED: 140 lbs./cu. ft. Adjust at Nozzle

## TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

$Al_2O_3$	SiO <sub>2</sub>	$Fe_2O_3$	TiO <sub>2</sub>	MgO	CaO	Alkalies	Other
57.1	37.6	0.9	1.6	0.1	2.2	0.2	0.3

## TYPICAL PHYSICAL PROPERTIES (gunned)

Prefired to	Modulus of	Cold Crushing	Linear Change
°F	Rupture, psi	Strength, psi	%
250	1,390 – 1,600	7,114	Nil
1500	1,225 – 1,654	7,070	-0.2
2000	1,375 – 1,739	8,500	-0.1
2500	2,658 - 2,760	15,000	+0.5

ABRASION LOSS AFTER 1500°F: <9 cc

**PACKAGING:** 55 lb. Bags, 72 per Pallet (3,960 lbs.)

126300 - 7/17/07

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.