



RENO REFRACTORIES, INC

RENO CAST SF 65 LC

TECHNICAL DATA SHEET

RENO CAST SF 65LC is a high alumina, high strength, extremely abrasion resistant, low cement castable that can be installed without vibration. Its high density and low porosity allows it to resist the attack of metal and slags.

SERVICE TEMPERATURE: 3100°F
MATERIAL REQUIRED FOR ESTIMATING: 160 lbs./cu. ft.
CASTING WATER (self flow): 5.5 - 6.5%
CASTING WATER (vibration): 5.5 - 6.0%

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	MgO	CaO	Alkalies	Other
64.9	30.4	0.9	1.9	0.1	1.1	0.2	Nil

TYPICAL PHYSICAL PROPERTIES

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
250	1,350	6,800	Nil
1500	2,200	12,100	-0.2
2500	2,900	13,900	+0.1

ABRASION LOSS AFTER 1500°F: (6.4% water) 4.7 cc

PACKAGING: 55 lb. Bags, 72 per Pallet (3,960 lbs.)

155500 – 2/11/09

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116
205.647.0240 | Toll Free 1.800.741.7366