



RENO REFRACTORIES, INC

RENO IRON CAST

TECHNICAL DATA SHEET

**RENO IRON CAST** is a high alumina-silicon carbide ultra low cement castable. It has high density, low porosity, high strength and excellent resistance to iron, slag, thermal shock and oxidation.

**RENO IRON CAST** is recommended for tilters, holding furnaces, troughs, torpedo and transfer ladles, as well as skimmer blocks. Can be cast, pumped or shotcreted.

**SERVICE TEMPERATURE:** 3000°F (Reducing)  
**MATERIAL REQUIRED FOR ESTIMATING:** 180 lbs/cf  
**WATER ADDITION:** 4.5 – 5.5%  
**STORAGE LIFE:** 1 year

**TYPICAL CHEMICAL ANALYSIS** (Calcined Basis)

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	TiO <sub>2</sub>	CaO	SIC + C	Other
79	9	2	1	8.8	0.5

**TYPICAL PHYSICAL PROPERTIES** (Reducing conditions above 250°F)

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
250	2,900	10,990	Nil
1,500	2,660	13,000	-0.1
2,500	2,422	12,650	-0.3

**HOT MOR @2500°F (ASTM C583 -- ORTON):** 1,276 psi  
**HOT MOR @2700°F (ASTM C583 -- ORTON):** 693 psi

**PACKAGING:** 1500 lb. bulk bags, 2 per pallet (3,000 lbs)  
3000 lb. bulk bags, 1 per pallet (3,000 lbs)

165600 – 9/26/14

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116  
205.647.0240 | Toll Free 1.800.741.7366