



RENO REFRACTORIES, INC

RENO PLASTIC 55 P

TECHNICAL DATA SHEET

RENO PLASTIC 55 P is a high alumina, low iron, phosphate bonded plastic with excellent workability. It exhibits high strengths and with its high density and low porosity, has excellent resistance to abrasion, metal penetration and slag attack.

SERVICE TEMPERATURE: 3000°F
MATERIAL REQUIRED FOR ESTIMATING: 155 lbs./cu. ft.

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	MgO	CaO	P ₂ O ₅	Alkalies
55.4	38	0.9	1.7	0.2	0.2	3.0	0.2

TYPICAL PHYSICAL PROPERTIES

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
600	200	1,300	-0.4
2000	750	3,200	-0.5
2500	850	4,600	-0.7
3000	1,700	7,100	-1.3

PACKAGING: 55 lb. Boxes, 60 per Pallet (3300 lbs.)

223900 – 10/5/01

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116
205.647.0240 | Toll Free 1.800.741.7366