



RENO REFRACTORIES, INC

MO 80 S

---

TECHNICAL DATA SHEET

---

**MO 80 S** is a wet, high duty, air setting mortar. It can be used to lay high and super duty fireclay brick and insulating firebrick to 2900°F. This economical mortar gives good bonding strength and provides strong air tight joints.

**SERVICE TEMPERATURE:** 2900°F  
**MATERIAL REQUIRED FOR ESTIMATING:** 450 lbs./M 9" Eq.  
**WATER REQUIRED - TROWELING:** Use as received

**TYPICAL CHEMICAL ANALYSIS** (Calcined Basis)

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	MgO	CaO	Alkalies	Other
22	73.1	0.4	0.9	0.1	0.1	3.4	-

**TYPICAL PHYSICAL PROPERTIES**

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
250	400-500	1,350-1,750	-0.5
1500	200-500	550-850	-0.3
2000	250-350	800-1,200	+0.3
2700	350-450	1,100-1,500	+0.2

**PACKAGING:** 60 lb. Pails, 48 per Pallet (2,880 lbs.)

413000 – 12/17/01

---

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, Inc. PO Box 201, Morris, Alabama 35116  
205.647.0240 | Toll Free 1.800.741.7366