



RENO REFRACTORIES, INC

RENO PUTTY 55

TECHNICAL DATA SHEET

RENO PUTTY 55 is a high alumina, phosphate bonded, patching refractory. It shows good resistance to slagging, spalling and abrasion.

RENO PUTTY 55 is particularly well suited for prolonging the life of existing refractories such as in ladles, tundishes and other metal contact areas.

SERVICE TEMPERATURE: 3000°F
MATERIAL REQUIRED FOR ESTIMATING: 150 lbs./cu. ft.
WATER REQUIRED: Use as received

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	MgO	CaO	P ₂ O ₅	Other
55	39	0.8	1.3	0.1	0.1	3.1	0.3

TYPICAL PHYSICAL PROPERTIES

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
250	225 – 325	825 – 1,100	-0.3
1500	525 – 700	1,600 – 2,000	-0.6
2000	675 – 750	2,100 – 2,500	-0.4
2500	850 – 1,000	3,400 – 3,800	+0.1

PACKAGING: 55 lb. Boxes, 60 per Pallet (3300 lbs.)
60 lb. Pails, 48 per Pallet (2880 lbs.)

421400 – 10/29/02

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116
205.647.0240 | Toll Free 1.800.741.7366