



RENO REFRACTORIES, INC

RENO PUTTY 90

TECHNICAL DATA SHEET

RENO PUTTY 90 is a high purity, phosphate bonded, extra high alumina plaster refractory. It has high strength and excellent workability.

RENO PUTTY 90 is particularly well suited for prolonging the life of existing refractories, especially in severe metal contact areas.

SERVICE TEMPERATURE: 3200°F
MATERIAL REQUIRED FOR ESTIMATING: 184 lbs/cf

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

| Al ₂ O ₃ | SiO ₂ | Fe ₂ O ₃ | MgO | CaO | P ₂ O ₅ |
|--------------------------------|------------------|--------------------------------|------|------|-------------------------------|
| 90-92 | 5-6 | <0.3 | <0.1 | <0.1 | 3.0 |

PACKAGING: 60 lb. Pails, 48 per Pallet (2880 lbs.)
55 lb. Cartons, 60 per Pallet (3300 lbs.)

427800 – 2/13/03

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116
205.647.0240 | Toll Free 1.800.741.7366