



RENO REFRACTORIES, INC

RENO 95 HS MORTAR

---

TECHNICAL DATA SHEET

---

**RENO 95 HS MORTAR** is a heat setting, high alumina, volume stable wet mortar.

**RENO 95 HS MORTAR** has excellent trowel ability, adherence and minimal cracking at high temperatures. Resists metal penetration and chemical attack. Stable in reducing atmospheres.

**SERVICE TEMPERATURE:** 2000-3200°F  
**WATER REQUIRED - TROWELING:** As desired

**TYPICAL CHEMICAL ANALYSIS**

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	MgO	CaO	Alkalies	P <sub>2</sub> O <sub>5</sub>
95.1	3.3	0.2	0.1	0.1	0.1	0.2	0.6

**PACKAGING:** 60 lb. Pails, 48 per Pallet (2880 lbs.)

428000 – 12/10/01

---

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116  
205.647.0240 | Toll Free 1.800.741.7366