



TECHNICAL DATA

RENO REFRACTORIES

CRM PATCH

CRM PATCH is a 70% alumina, 7.5% chrome, phosphate bonded, wet patching mortar for severe service conditions. It has good strength, particularly at the lower temperatures. This product is used for patch and as a protective coating on existing refractories.

SERVICE TEMPERATURE:	3400°F
MATERIAL REQUIRED FOR ESTIMATING:	550 lbs./M 9" Eq.
WATER REQUIRED - TROWELING:	Use as received

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	MgO	CaO	P ₂ O ₅	Cr ₂ O ₃
65	16	1.0	1.5	0.1	0.1	8	7.5

PACKAGING: 60 lb. Pails, 48 per Pallet

428900

4/4/09

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.