



**RENO REFRACTORIES, INC**

**RENO AluSHIELD NC 65**

**TECHNICAL DATA SHEET**

**RENO AluSHIELD NC 65** is a high alumina, no-cement, non-wetting castable designed to be installed by casting, pumping or shotcreting.

**Features:**

- Excellent resistance to aluminum penetration
- Resists alkali attack
- Abrasion resistance
- Excellent thermal shock resistance
- Less than 1.8% crystalline (free) silica
- Applications include aluminum contact areas in melters, holders, troughs and ladles

**SERVICE TEMPERATURE:**

2800°F

**MATERIAL REQUIRED FOR ESTIMATING:**

160 lbs./ft<sup>3</sup>

**BINDER ADDITION:**

9.5-10.5%

**TYPICAL CHEMICAL ANALYSIS (Calcined Basis)**

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	Other
63-65	32-35	<1.0	3

**TYPICAL PHYSICAL PROPERTIES**

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %	Thermal Cond. Btu-in/hr-ft <sup>2</sup> °F
250	1,200-1,316	5,600-6,550	-0.1	10.3
1000	1,300-1,390	5,900-8,300	0.0	--
1500	1,800-2,230	8,500-10,100	-0.1	11.05
2000	4,190-4,800	>14,200	0.0	11.11
2500	5,380-6,300	>14,100	+0.6	11.04

**ABRASION LOSS After 1500°F:** <5 cc

**ABRASION LOSS After 2000°F:** <5 cc

**ALUMINUM CUP TEST RATING:** Excellent

**PACKAGING:** 1500 lb. bulk bags, 2 per pallet (3000 lbs)

2000 lb. bulk bags, 2 per pallet (4000 lbs)

17-054

604065 – 4/30/2017

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

**Reno Refractories, Inc. PO Box 201, Morris, Alabama 35116  
205.647.0240 | Toll Free 1.800.741.7366**