



TECHNICAL DATA SHEET

Reno ElectroShot™ 370 is a mullite based, low moisture castable designed to be installed by the shotcrete process.

- Based on Reno’s proprietary Electro Chemical bond
• Utilizes engineered high quality Mullite aggregate for greater corrosion resistance.
• Micro porosity of bond phase has greatly reduced reactivity to corrosive vapors in the process.
• High hot strength and abrasion resistance.
• Low porosity and permeability for reduced penetration and reaction with molten metals, slags, and vapors.
• Recommended for molten iron transport vessels such as ladles, spouts, covers, etc. where low to moderate slag is present.

Service Temperature: 3000°F
Storage Life: 6 months
Electrolyte Type: E3
Addition Quantity: 4.0-5.0% (wt.)
Wt. Required for Estimating: 156 lb/ft³
Storage Life: 6 months

TYPICAL CHEMICAL ANALYSIS (% Calcined Basis)

Table with 5 columns: Al2O3, SiO2, Fe2O3, TiO2, Other. Values: 70, 27, 0.7, 2, 0.35

TYPICAL PHYSICAL PROPERTIES

Table with 9 columns: Prefire Temperature, Modulus of Rupture, Cold Crushing Strength, Density, Porosity, Linear Change, Permeability, Thermal k, Surface Area. Rows for temperatures 250, 750, 1500, 2000, 2500, 2800.

Thermal Expansion Coefficient: 2.85E-6 in/in/°F (ASTM C832)
Thermal Cycle Loss (after 2000°F): 11.9% MOR Loss (ASTM C-1171)

Abrasion Loss After 1500°F: 2.5 cc (ASTM C704)
Abrasion Loss After 2500°F: 2.5 cc (ASTM C704)

PACKAGING: 55 lb. Bags, 72 per Pallet (3960 lbs.) 1500 lb. Bags, 2 per Pallet (3000 lbs.) 2000 lb. Bags, 2 per Pallet (4000 lbs.)

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.