



RENO REFRACTORIES, INC

RENO ALL MAG

TECHNICAL DATA SHEET

RENO ALL MAG is sintered magnesia, air setting mortar for temperatures to 3000°F.

RENO ALL MAG is shipped dry and water is added to achieve the desired consistency.

SERVICE TEMPERATURE:	3000°F
MATERIAL REQUIRED FOR ESTIMATING:	625 lbs. /M 9" Eq.
WATER REQUIRED - TROWELING:	~20-25%
POTTABLE TIME:	~1 hour

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	MgO	CaO	Alkalies	P ₂ O ₅
0.5	2.1	0.2	94.3	0.9	0.7	1.3

PACKAGING: 55 lb. bags, 72 per Pallet (3960 lbs.)

438700 – 9/23/21

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116
205.647.0240 | Toll Free 1.800.741.7366