



TECHNICAL DATA SHEET

Reno Mag Cast 757 CR is a no cement castable for use where a basic chrome containing refractory is needed.

Service Temperature: 3100°F/1748°F
Liquid Type: Water
Addition Quantity: 5.50-5.75%

Wt. Required for Estimating: 173 lbs/ft³
Storage Life: 6 months

TYPICAL CHEMICAL ANALYSIS (% Calcined Basis)

Table with 9 columns: MgO, Al2O3, SiO2, Fe2O3, TiO2, CaO, Cr2O3, Alkalies, P2O5. Values range from 0.02 to 75.47.

TYPICAL COLD PHYSICAL PROPERTIES

Table with 10 columns: Prefired to °F, Cold Modulus of Rupture (psi), Cold Crushing Strength (psi), Density (pcf), Porosity (%), Linear Change (%), Abrasion Loss (cc), Thermal Shock Loss (%), Permeability (mDarcys), Surface Area (m²/g). Values range from 0.043 to 11.341.

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.