RENO AluSHIELD 60 QH

TECHNICAL DATA SHEET

RENO AluSHIELD 60 QH is a low iron, low cement alumina castable that can be cast or pumped.

FEATURES:

- Non-wetting to aluminum
- Excellent hot strength at 1500°F
- Low porosity and permeability, low thermal expansion
- Applications include aluminum furnaces, ladles, troughs, and rotary dross furnaces

SERVICE TEMPERATURE: 2500°F

MIXING WATER: 5.0 – 5.5% (Casting) 5.5 – 6.0% (Pumping)

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

| Al ₂ O ₃ | SiO ₂ | Fe ₂ O ₃ | TiO ₂ | MgO | CaO | Alkalies | Other |
|--------------------------------|------------------|--------------------------------|------------------|------|-----|----------|-------|
| 60.9 | 34.4 | 0.8 | 1.3 | 0.07 | 1.5 | 0.2 | 0.8 |

TYPICAL PHYSICAL PROPERTIES (Cast)

| Prefired to °F | Density pcf | Linear Change % | Modulus of Rupture, psi | Cold Crushing Strength, psi | Abrasion Loss cc |
|-------------------|----------------|--------------------|----------------------------|--------------------------------|---------------------|
| 250 | 153 | -0.1 | 1,895 | 5,445 | |
| 1000 | 153 | -0.1 | 1,655 | 4,400 | 3.2 |
| 1500 | 152 | +0.3 | 4,000 | 10,825 | 3.8 |
| 2000 | 152 | +0.4 | 3,000 | 6,840 | 4.6 |
| 2500 | 152 | +0.5 | 3,540 | 8,500 | |

TYPICAL PHYSICAL PROPERTIES (Pump)

| Prefired to °F | Density pcf | Porosity % | Linear Change % | Modulus of Rupture, psi | Cold Crushing Strength, psi |
|----------------|----------------|---------------|--------------------|----------------------------|--------------------------------|
| 250 | 152 | 11.9 | -0.2 | 1,890 | 7,835 |
| 1500 | 150 | 15.9 | -0.6 | 3,175 | 9,050 |
| 2000 | 146 | 15.8 | +0.1 | 4,770 | 12,710 |
| 2500 | 144 | 19.6 | +1.2 | 4,575 | 12,450 |

HOT MODULUS OF RUPTURE, 1500°F: 4,190 psi (Cast)

COEFFICIENT OF THERMAL EXPANSION: 2.13 x 10⁻⁶ in/in/°F (Cast)

17-008 603060 - 3/1/17

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.