

Reno Gun ES

TECHNICAL DATA SHEET

Reno Cast ES-C is special formulated low iron gun mix that excellent abrasion resistance and high strength where for extreme petrochemical applications. **Reno Cast ES-C** is an excellent choice for operating conditions where abrasion and high strength low properties are required.

Service Temperature: 2700°F / 1370°C Wt. Required for Estimating: 130 lb/ft³

 $2080\;kg/m^3$

Liquid Type: Water Storage Life: 6 months

Water for Casting: 9.25 to 9.75% by weight

TYPICAL CHEMICAL ANALYSIS(% Calcined Basis)

| Al_2O_3 | SiO ₂ | Fe ₂ O ₃ | TiO ₂ | CaO | Alkalis |
|-----------|------------------|--------------------------------|------------------|-----|---------|
| 53.8 | 35.9 | 0.8 | 1.3 | 7.6 | 0.4 |

TYPICAL COLD PHYSICAL PROPERTIES

| Temperature °F | Cold Modulus of Rupture (psi) | Cold Crushing Strength (psi) | Density (lb/ft³) | PLC (%) | Abrasion Loss (cc) |
|----------------|--|------------------------------------|---------------------|---------------|--------------------------|
| 1500 | 1300 - 1800 | 9000 - 13000 | 128 - 134 | -0.0 to - 0.3 | <10 (Typical 7 - 9) |

| Temperature °C | Cold Modulus of Rupture (MPa) | Cold Crushing Strength (MPa) | Density (kg/m³) | PLC (%) | Abrasion Loss (cc) |
|----------------|--|------------------------------------|--------------------|---------------|--------------------------|
| 815°C | 8.9 – 12.4 | 62 - 90 | 2050 - 2145 | -0.0 to - 0.3 | <10 (Typical 7 - 9) |

TYPICAL HOT PHYSICAL PROPERTIES

| Temperature | Thermal Conductivity |
|-------------|----------------------|
| °F | (BTU/ft²/hr/in/°F) |
| 500 | 7.0 |
| 1000 | 7.8 |
| 1500 | 8.2 |

| Temperature | Thermal Conductivity |
|-------------|----------------------|
| °C | (W/m K) |
| 260 | 1.00 |
| 538 | 1.12 |
| 815 | 1.18 |

PACKAGING: 50 lb. Bags, 40 per Pallet (2,000 lbs.)

RB PIN# 611700 6/30/22