



RENO REFRACTORIES, INC

Reno ASAP Cast 75 ABR

TECHNICAL DATA SHEET

Reno ASAP Cast 75 ABR is a 3200°F (1760°C) high strength, low cement, hydraulically bonded castable that provides superior abrasion resistance and extraordinary strength. **Reno ASAP Cast 75 ABR** is installed via vibration casting and is designed for use in burner pipes, target walls and other high abrasion application when dry out the refractory linings are complicated and / or the process equipment is required back in service immediately. Use **Reno ASAP Pump 75 ABR** applications when pumping is required.

Service Temperature:	32000°F 1760°C	Dry Weight for Mixing :	174 lbs./ft ³ 2,785 kg/m ³
Liquid Type:	Water	Shelf Life:	6 months
Liquid Quantity:	4 to 5% by weight		

TYPICAL CHEMICAL ANALYSIS (% Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	MgO	Alkalis	Other
75	10	2	3	2	.25	0.1	9

TYPICAL COLD PHYSICAL PROPERTIES

Temperature °F	Cold Modulus of Rupture lb/ft ²	Cold Crushing Strength lb/ft ²	Density lb/ft ²	Linear Change (%)	Abrasion Loss (cc)
1500°F	3,500	+21,000	174	0 to -0.30	< 3

Fire	Cold Modulus of Rupture MPa	Cold Crushing Strength MPa	Density kg/m ³	Linear Change (%)	Abrasion Loss (cc)
815°C	24	+145	2785	0 to -0.30	< 3

PACKAGING: 55 lb. (25 Kg) Bags, 72 per Pallet @ 3,960 lbs (1,800 kg)

RB

PIN#613520

7/20/2022

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116 205.647.0240 | Toll Free 1.800.741.7366