



RENO REFRACTORIES, INC

RENO AluSHIELD 6810 SC

TECHNICAL DATA SHEET

RENO AluSHIELD 6810 SC is an alumina based, silicon carbide containing, non-wetting refractory. Recommended in lower sidewalls, bellybands, hearths and ramps.

FEATURES:

- Free silica is less than 0.6%
- Excellent non-wetting
- Excellent abrasion resistance
- Excellent alkali resistance

SERVICE TEMPERATURE:

2500°F

MATERIAL REQUIRED FOR ESTIMATING:

175 lbs./ft³

WATER ADDITION:

4.5-5.5%

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al ₂ O ₃	SiC	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	Alkali	Other
68	10	12.5	1.5	4.5	1.5	< 0.25	2

TYPICAL PHYSICAL PROPERTIES

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Density (pcf)	Linear Change (%)	Porosity %
Green	1,000	10,790	179	-0.06	0
250	1,761	9,162	178	-0.11	9.12
750	1,966	10,023	175	-0.03	14.22
1500	3,278	13,197	177	-0.10	15.95
2200	3,730	16,134	173	-0.04	14.85

HOT MOR @ 1500°F (ORTON):

3,796 psi

HOT MOR @ 2500°F (ORTON):

2,473 psi

ABRASION LOSS After 1500°F:

4 cc

THERMAL Cycle After 2000°F:

30% MOR Loss (ASTM C-1171)

ALUMINUM CUP TEST RATING:

Excellent

ALKALI RESISTANCE TEST RATING:

Excellent

PACKAGING: 55 lb. Bags, 72 per Pallet (3960) lbs.

23-080

603625 – 04/22/2024

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116
205.647.0240 | Toll Free 1.800.741.7366