RENO REFRACTORIES, INC **PT 85 PF**

TECHNICAL DATA SHEET

PT 85 PF is a high purity, phosphate bonded, putty consistency refractory. Its high alumina and excellent workability makes **PT 85 PF** ideal for patching and maintaining contours of existing refractory linings, especially in metal contact areas.

SERVICE TEMPERATURE: 3100°F
WATER REQUIRED: Use as received

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al_2O_3	SiO_2	Fe_2O_3	TiO_2	MgO	CaO	P_2O_5	Alkalies
84.2	8.6	1.0	2.1	0.1	Nil	3.5	0.5

PACKAGING: 55 lb. Pails, 24 per Pallet (1,320 lbs.)

426000 – 6/28/13

The data presented represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specification purposes.

Reno Refractories, PO Box 201, Morris, Alabama 35116
205.647.0240 | Toll Free 1.800.741.7366